

T153-840 (En3T153-840Z275Vim.ppf / 733027.53074444)

**RUUKKI**

**T153-40L-840 - Z275 - Positive - Narrow flange against support.**

No.	Thickness		Weight	Limit yield point	Tensile strenght	Zinc	Coating
	nominal	core					
A	t <sub>nom</sub>	t <sub>core</sub>	g	fy	fu	Zn	SP 15
B	mm	mm	kg/m <sup>2</sup>	MPa	MPa	g/m <sup>2</sup>	μm
1.	0.60	0.56	8.41	320.0	390.0	100	25
2.	0.70	0.66	9.81	350.0	420.0	100	25
3.	0.75	0.71	10.51	350.0	420.0	100	25
4.	0.80	0.76	11.21	350.0	420.0	100	25
5.	0.88	0.84	12.34	350.0	420.0	100	25
6.	0.90	0.86	12.62	350.0	420.0	100	25
7.	1.00	0.96	14.02	350.0	420.0	100	25
8.	1.10	1.06	15.42	350.0	420.0	100	25
9.	1.13	1.09	15.84	350.0	420.0	100	25
10.	1.20	1.16	16.82	350.0	420.0	100	25
11.	1.25	1.21	17.52	350.0	420.0	100	25
12.	1.50	1.46	21.03	350.0	420.0	100	25