

T45-30L-905 - Z275 - Perforated - Positive - Narrow flange against support.

RUUKKI

No.	Thickness		Weight	Limit yield point	Tensile strenght	Zinc	Coating
	nominal	core					
A	t _{nom}	t _{core}	g	fy	fu	Zn	SP 15
B	mm	mm	kg/m ²	MPa	MPa	g/m ²	μm
1.	0.50	0.46	5.42	280.0	360.0	275	25
2.	0.60	0.56	6.51	280.0	360.0	275	25
3.	0.70	0.66	7.59	350.0	420.0	275	25
4.	0.80	0.76	8.67	350.0	420.0	275	25
5.	0.90	0.86	9.76	350.0	420.0	275	25
6.	1.00	0.96	10.84	350.0	420.0	275	25